

3M Crystalline Folien – Kombination mit Abarth 500 (44% VLT)

Folie	Folien-VLT	Gesamt-VLT	TSER	IR-Reduktion	Praxisbewertung
CR90	90%	39.6%	34%	~90%	fast Serie
CR80	80%	35.2%	43%	~95%	OEM+
CR70	70%	30.8%	50%	~97%	sehr sinnvoll
CR60	60%	26.4%	54%	~97%	guter Kompromiss
CR50	50%	22.0%	57%	~97%	Sweet Spot
CR40	40%	17.6%	60%	~97%	dunkel
CR30	30%	13.2%	63%	~97-99%	sehr dunkel
CR25	25%	11.0%	64%	~99%	extrem
CR20	20%	8.8%	65%	~99%	sehr extrem
CR15	15%	6.6%	66%	~99%	Show
CR05	5%	2.2%	67%	~99%	Blackout